Specif-i Data Sheet



INEX>RENDERBOARD - Armawall Armashield Low Profile INEX>WALLBOARD IRB03

Э Job Details

Client Reference No. Project Date

Specifications

Substrator)/WALLBOARD: Smooth & Rough Surface
Substrate.	WALLDUARD. SHOULI & RUUYH SUHALE

New/Repaint: Texture New Quality:

Interior/Exterior: Texture

Surface Preparation

Inex Render Boards must be installed as per manufacturer's recommendations. Surfaces to be coated must be free from all dirt, dust, grease, grim and previous coatings. Wash the surface with detergent and water. Machine sand the surface evenly with a suitable medium grade sandpaper and dust off. The surface must be dry before applying undiluted Armawall Sealer Bonder. The moisture content of the substrate must not exceed 15% (WME) wood moisture equivalent before, during or after application of the Armawall Texture Coating System.

1st coat: Armawall Sealer/Bonder Clear Undiluted (D240)

Application: Brush, Roller	Spreading Rate sqm/litre: 12
Reducer/Washup: iCoat Thinner LO-2	Recoat Time: 2

Dry Film Thickness: 0

2nd coat: Armawall Armashield (D0245)

Application: Nap Roller	Spreading Rate sqm/litre: 8
Reducer/Washup: Water	Recoat Time: 4
Dry Film Thickness: 0	

3rd coat: Armawall Armashield (D0245)

Application: Nap Roller	Spreading Rate sqm/litre: 8
Reducer/Washup: Water	Recoat Time: 4
Dry Film Thickness: 0	

DISCLAIMER

The technical information and suggestions for use and application presented herein represent the best information available to use and are believed to be reliable. They should not, however, be construed as controlling suggestions and there is no warranty of performance of our materials either expressed or implied. We urge that users of our materials conduct confirmatory tests to determine that final suitability for their specific end users.

Specifications and information for:

