

Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Everyday Life	Dawber			SA	230	110	76	DW1	2.8	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	Exposure Grade	Slight	Slight	-
Everyday Life	Discover			SA	230	110	76	DW1	2.8	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	Exposure Grade	Slight	Slight	-
Everyday Life	Empower			SA	230	110	76	DW1	2.8	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	Exposure Grade	Slight	Slight	-
Everyday Life	Inspire			SA	230	110	76	DW1	2.8	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	Exposure Grade	Slight	Slight	-

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 April 2021



BOWRAL BRICKS



nubrik
authentic brickwork