

Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	Division	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
San Selmo Smoked	Cloudy Silver Facing Corner Unit – Standard			Import	230	110	76	DW0	1.1	Solid	NA	1008	>10	<15	<3.0	<1.0	General Purpose	Slight	Slight	NA
San Selmo Smoked	Cloudy Silver Facing Unit – Standard			Import	230	18	76	DW0	0.5	Solid	48.5	2160	>10	<15	<3.0	<1.0	General Purpose	Slight	Slight	NA
San Selmo Smoked	Grey Cashmere Facing Corner Unit – Standard			Import	230	110	76	DW0	1.1	Solid	NA	1008	>10	<15	<3.0	<1.0	General Purpose	Slight	Slight	NA
San Selmo Smoked	Grey Cashmere Facing Unit – Standard			Import	230	18	76	DW0	0.5	Solid	48.5	2160	>10	<15	<3.0	<1.0	General Purpose	Slight	Slight	NA
San Selmo Smoked	Opaque Slate Facing Corner Unit – Standard			Import	230	110	76	DW0	1.1	Solid	NA	1008	>10	<15	<3.0	<1.0	General Purpose	Slight	Slight	NA
San Selmo Smoked	Opaque Slate Facing Unit – Standard			Import	230	18	76	DW0	0.5	Solid	48.5	2160	>10	<15	<3.0	<1.0	General Purpose	Slight	Slight	NA
San Selmo Smoked	Wild Storm Facing Corner Unit – Standard			Import	230	110	76	DW0	1.1	Solid	NA	1008	>10	<15	<3.0	<1.0	General Purpose	Slight	Slight	NA
San Selmo Smoked	Wild Storm Facing Unit – Standard			Import	230	18	76	DW0	0.5	Solid	48.5	2160	>10	<15	<3.0	<1.0	General Purpose	Slight	Slight	NA

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 October 2020



BORAL BRICKS



nubrik[®]
 authentic brickwork