















Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Urban One	Biscotti			SA	230	110	76	DW1	2.8	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	Exposure Grade	Slight	Slight	-
Urban One	Char			SA	230	110	76	DW1	2.8	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	Exposure Grade	Slight	Slight	-
Urban One	Chiffon			SA	230	110	76	DW1	2.8	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	General Purpose	Slight	Slight	-
Urban One	Latte			SA	230	110	76	DW1	3	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	Exposure Grade	Slight	Slight	-
Urban One	Muscat Grey			SA	230	110	76	DW1	2.8	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	Exposure Grade	Slight	Slight	-
Urban One	Praline			SA	230	110	76	DW1	2.8	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	Exposure Grade	Slight	Slight	-
Urban One	Seed			SA	230	110	76	DW1	2.8	<30	48.5	400	>20	<10	0.5 - 1.5	<1.2	General Purpose	Slight	Slight	-

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 April 2021



BORAL BRICKS



nubrik
authentic brickwork