













# Technical Data Sheet

**BRICKWORKS**

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Wilderness Design	Blackberry			NSW	230	110	76	DW1	2.8	<38	48.5	400	>10	<10	2.0	<1.2	Exposure Grade	Slight	Slight	-
Wilderness Design	Blackbutt			NSW	230	110	76	DW1	2.8	<38	48.5	400	>10	<10	2.0	<1.2	Exposure Grade	Slight	Slight	-
Wilderness Design	Blue Gum			NSW	230	110	76	DW1	2.8	<38	48.5	400	>10	<10	2.0	<1.2	Exposure Grade	Slight	Slight	-
Wilderness Design	Grey Gum			NSW	230	110	76	DW1	2.8	<38	48.5	400	>10	<10	2.0	<1.2	Exposure Grade	Slight	Slight	-
Wilderness Design	Rosewood			NSW	230	110	76	DW1	2.8	<38	48.5	400	>10	<10	2.0	<1.2	Exposure Grade	Slight	Slight	-
Wilderness Design	Silver Birch			NSW	230	110	76	DW1	2.8	<38	48.5	400	>10	<10	2.0	<1.2	Exposure Grade	Slight	Slight	-

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 November 2020



BOWRAL BRICKS



nubrik