



## Product Range: Bowral Blends

**Product Name:** Burradoo | **Size:** 230 × 110 × 76mm | **Manufactured:** NSW




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.8
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	<15
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	3.0 - 8.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	Solid
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	NA
Durability Class	Exposure Grade



## Product Range: Bowral Blends

**Product Name:** Bargo | **Size:** 230 × 110 × 76mm | **Manufactured:** NSW




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.8
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	<15
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	3.0 - 8.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	Solid
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	NA
Durability Class	Exposure Grade



## Product Range: Bowral Blends

**Product Name:** Exeter | **Size:** 230 × 110 × 76mm | **Manufactured:** NSW




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.8
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	<15
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	3.0 - 8.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	Solid
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	NA
Durability Class	Exposure Grade



## Product Range: Bowral Blends

**Product Name:** Berrima | **Size:** 230 × 110 × 76mm | **Manufactured:** NSW




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.8
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	<15
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	3.0 - 8.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	Solid
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	NA
Durability Class	Exposure Grade



## Product Range: Bowral Blends

**Product Name:** Kangaloon | **Size:** 230 × 110 × 76mm | **Manufactured:** NSW




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.8
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	<15
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	3.0 - 8.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	Solid
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	NA
Durability Class	Exposure Grade



## Product Range: Bowral Blends

**Product Name:** Hill Top | **Size:** 230 × 110 × 76mm | **Manufactured:** NSW




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.8
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	<15
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	3.0 - 8.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	Solid
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	NA
Durability Class	Exposure Grade



## Product Range: Bowral Blends

**Product Name:** Wilton | **Size:** 230 × 110 × 76mm | **Manufactured:** NSW




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.8
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	<15
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	3.0 - 8.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	Solid
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	NA
Durability Class	Exposure Grade



## Product Range: Bowral Blends

**Product Name:** Mt Broughton | **Size:** 230 × 110 × 76mm | **Manufactured:** NSW




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.8
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	<15
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	3.0 - 8.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	Solid
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	NA
Durability Class	Exposure Grade





## Product Range: Bowral Blends

**Product Name:** Picton | **Size:** 230 × 110 × 76mm | **Manufactured:** NSW



Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.8
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>12
Maximum Cold Water Absorption (%)	<15
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	3.0 - 8.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	Solid
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	NA
Durability Class	Exposure Grade

