

























Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Overland	Cradle (Pristine)			TAS	230	110	76	DW1	3.5	<20	48.5	384	>15	<8	0.5 - 1.5	<1.0	General Purpose	Slight	Slight	Dark
Overland	Cradle (Rugged)			TAS	230	110	76	DW1	3.5	<20	48.5	384	>15	<8	0.5 - 1.5	<1.0	General Purpose	Slight	Slight	Dark
Overland	Freycinet (Pristine)			TAS	230	110	76	DW1	3.5	<20	48.5	384	>15	<13	1.0 - 2.5	<1.0	General Purpose	Slight	Slight	Dark
Overland	Freycinet (Rugged)			TAS	230	110	76	DW1	3.5	<20	48.5	384	>15	<13	1.0 - 2.5	<1.0	General Purpose	Slight	Slight	Dark
Overland	Tarkine (Pristine)			TAS	230	110	76	DW1	3.5	<20	48.5	384	>15	<12	1.5 - 3.0	<1.0	General Purpose	Slight	Slight	Medium
Overland	Tarkine (Rugged)			TAS	230	110	76	DW1	3.5	<20	48.5	384	>15	<12	1.5 - 3.0	<1.0	General Purpose	Slight	Slight	Medium
Overland	Huon (Pristine)			TAS	230	110	76	DW1	3.5	<20	48.5	384	>15	<12	1.5 - 3.0	<1.0	General Purpose	Slight	Slight	Dark
Overland	Huon (Rugged)			TAS	230	110	76	DW1	3.5	<20	48.5	384	>15	<12	1.5 - 3.0	<1.0	General Purpose	Slight	Slight	Dark
Overland	Bruny (Pristine)			TAS	230	110	76	DW1	3.4	<20	48.5	384	>12	<12	0.5 - 2.5	<1.0	General Purpose	Slight	Slight	Dark
Overland	Bruny (Rugged)			TAS	230	110	76	DW1	3.4	<20	48.5	384	>12	<12	0.5 - 2.5	<1.0	General Purpose	Slight	Slight	Dark
Overland	Flinders (Pristine)			TAS	230	110	76	DW1	3.3	<20	48.5	384	>15	<12	0.5 - 2.0	<1.0	General Purpose	Slight	Slight	Dark
Overland	Flinders (Rugged)			TAS	230	110	76	DW1	3.3	<20	48.5	384	>15	<12	0.5 - 2.0	<1.0	General Purpose	Slight	Slight	Dark

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

August 2021

DANIEL ROBERTSON