



## Product Range: Overland

**Product Name:** Cradle (Pristine) | **Size:** 230 × 110 x76mm | **Manufactured:** TAS



Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.5
Units per Square Metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<8
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	0.5 - 1.5
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	<20
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
Durability Class	General Purpose


This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020






## Product Range: Overland

**Product Name:** Frecinet (Pristine) | **Size:** 230 × 110 x76mm | **Manufactured:** TAS




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.5
Units per Square Metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<13
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	1.0 - 2.5
Estimated 15 year Coefficient of Expansion (e'Factor)	<1.0
Core Volume (%)	<20
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
High Pressure Cleaning Test	NA
Durability Class	General Purpose

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020



## Product Range: Overland

**Product Name:** Frecinet (Rugged) | **Size:** 230 × 110 x76mm | **Manufactured:** TAS




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.5
Units per Square Metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<13
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	1.0 - 2.5
Estimated 15 year Coefficient of Expansion (e'Factor)	<1.0
Core Volume (%)	<20
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
High Pressure Cleaning Test	NA
Durability Class	General Purpose

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020




## Product Range: Overland

**Product Name:** Tarkine (Pristine) | **Size:** 230 × 110 x76mm | **Manufactured:** TAS




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.5
Units per Square Metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<12
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	1.5 - 3.0
Estimated 15 year Coefficient of Expansion (e'Factor)	<1.0
Core Volume (%)	<20
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
High Pressure Cleaning Test	NA
Durability Class	General Purpose

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020



## Product Range: Overland

**Product Name:** Tarkine (Rugged) | **Size:** 230 × 110 x76mm | **Manufactured:** TAS




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.5
Units per Square Metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<12
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	1.5 - 3.0
Estimated 15 year Coefficient of Expansion (e'Factor)	<1.0
Core Volume (%)	<20
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
High Pressure Cleaning Test	NA
Durability Class	General Purpose

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020



## Product Range: Overland

**Product Name:** Huon (Pristine) | **Size:** 230 × 110 x76mm | **Manufactured:** TAS




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.5
Units per Square Metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<12
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	1.5 - 3.0
Estimated 15 year Coefficient of Expansion (e'Factor)	<1.0
Core Volume (%)	<20
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
High Pressure Cleaning Test	NA
Durability Class	General Purpose

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020



## Product Range: Overland

**Product Name:** Huon (Rugged) | **Size:** 230 × 110 x76mm | **Manufactured:** TAS



Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW1
Average Weight / Unit (kg)	3.5
Units per Square Metre	48.5
Pack Size	384
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<12
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	1.5 - 3.0
Estimated 15 year Coefficient of Expansion (e'Factor)	<1.0
Core Volume (%)	<20
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
High Pressure Cleaning Test	NA
Durability Class	General Purpose

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020

