

# Technical Data Sheet

| Product Range | Product Name | Dimensional Illustration  | Swatch  | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Average Weight/ Unit (kg) | Core Volume (%) | Units Per m Squared | Pack Size | Characteristic Unconfined Compressive Strength (fuc) (Mpa) | Cold Water Absorption (%) | Initial Rate of Absorption (IRA) | eFactor | Durability Class | Liability to Effloresce | Lime Pitting Liability | Solar Absorptance Rating |
|---------------|--------------|---|---|-------|-------------|------------|-------------|----------------------|---------------------------|-----------------|---------------------|-----------|--|---------------------------|----------------------------------|---------|------------------|-------------------------|------------------------|--------------------------|
| Forest        | Cleland      |  |  | SA    | 230         | 110        | 76          | DW1                  | 2.775                     | <33             | 48.5                | 400       | >20  | <10                       | 0.5 - 1.5                        | <1.2    | Exposure Gade    | Slight                  | Slight                 | -                        |
| Forest        | Morialta     |  |  | SA    | 230         | 110        | 76          | DW1                  | 2.775                     | <33             | 48.5                | 400       | >20  | <10                       | 0.5 - 1.5                        | <1.2    | Exposure Gade    | Slight                  | Slight                 | -                        |
| Forest        | Penola       |  |  | SA    | 230         | 110        | 76          | DW1                  | 2.775                     | <33             | 48.5                | 400       | >20  | <10                       | 0.5 - 1.5                        | <1.2    | Exposure Gade    | Slight                  | Slight                 | -                        |
| Forest        | Black Forest |  |  | SA    | 230         | 110        | 76          | DW1                  | 2.775                     | <33             | 48.5                | 400       | >20  | <10                       | 0.5 - 1.5                        | <1.2    | Exposure Gade    | Slight                  | Slight                 | -                        |

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2021