


Product Range: La Paloma

Product Name: Tash | Size: 236 × 114 × 65mm | Manufactured: Imported




Typical Properties	
Length (mm)	236mm
Width (mm)	114mm
Height (mm)	65mm
Dimensional Category	DW1
Average Weight / Unit (kg)	2.4
Units per Square Metre	55
Pack Size	448
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<8
Initial Rate of Absorption (IRA) (kg/m ² min)	<0.8
Coefficient of Expansion e'Factor (mm/m)	<1.2
Core Volume (%)	<40
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 October 2020

Product Range: La Paloma

Product Name: Curved | **Size:** 236 × 114 × 50mm | **Manufactured:** Imported




Typical Properties	
Length (mm)	236mm
Width (mm)	114mm
Height (mm)	50mm
Dimensional Category	DW1
Average Weight / Unit (kg)	1.8
Units per Square Metre	68
Pack Size	608
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<8
Initial Rate of Absorption (IRA) (kg/m ² min)	<0.8
Coefficient of Expansion e'Factor (mm/m)	<1.2
Core Volume (%)	<40
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 October 2020

Product Range: La Paloma

Product Name: Comb | **Size:** 217 × 114 × 65mm | **Manufactured:** Imported



Typical Properties	
Length (mm)	217mm
Width (mm)	114mm
Height (mm)	65mm
Dimensional Category	DW1
Average Weight / Unit (kg)	2.1
Units per Square Metre	59
Pack Size	468
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<8
Initial Rate of Absorption (IRA) (kg/m ² min)	<0.8
Coefficient of Expansion e'Factor (mm/m)	<1.2
Core Volume (%)	<40
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 October 2020