


## Product Range: Laneway

**Product Name:** Warehouse Red | **Size:** 230 × 110 x76mm | **Manufactured:** VIC




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW0
Average Weight / Unit (kg)	4.1
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<10
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	0.5 - 2.5
Coefficient of Expansion e'Factor (mm/m)	<1.2
Core Volume (%)	<10
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020

## Product Range: Laneway

**Product Name:** Brunswick Blue | **Size:** 230 × 110 x76mm | **Manufactured:** VIC




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW0
Average Weight / Unit (kg)	4.1
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<10
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	0.5 - 2.5
Coefficient of Expansion e'Factor (mm/m)	<1.2
Core Volume (%)	<10
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020

## Product Range: Laneway

Product Name: Fitzroy Blend | Size: 230 × 110 x76mm | Manufactured: VIC




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW0
Average Weight / Unit (kg)	4.1
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<10
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	0.5 - 2.5
Coefficient of Expansion e'Factor (mm/m)	<1.2
Core Volume (%)	<10
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020

## Product Range: Laneway

**Product Name:** Hardware Grey | **Size:** 230 × 110 x76mm | **Manufactured:** VIC




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW0
Average Weight / Unit (kg)	4.1
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<10
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	0.5 - 2.5
Coefficient of Expansion e'Factor (mm/m)	<1.2
Core Volume (%)	<10
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020

## Product Range: Laneway

**Product Name:** Hosier Bluestone | **Size:** 230 × 110 x76mm | **Manufactured:** VIC




Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW0
Average Weight / Unit (kg)	4.1
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<10
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	0.5 - 2.5
Coefficient of Expansion e'Factor (mm/m)	<1.2
Core Volume (%)	<10
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020

**Product Range: Laneway**

**Product Name: Weathered Red | Size: 230 x 110 x76mm | Manufactured: VIC**



Typical Properties	
Length (mm)	230mm
Width (mm)	110mm
Height (mm)	76mm
Dimensional Category	DW0
Average Weight / Unit (kg)	4.1
Units per Square Metre	48.5
Pack Size	400
Characteristic Unconfined Compressive Strength (f'uc) MPa	>15
Maximum Cold Water Absorption (%)	<10
Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	0.5 - 2.5
Coefficient of Expansion e'Factor (mm/m)	<1.2
Core Volume (%)	<10
Liability to Efflorescence	Slight
Lime Pitting Liability	Slight
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2020