

Technical Data Sheet

| Product Range | Product Name | Dimensional Illustration | Swatch | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Average Weight/ Unit (kg) | Core Volume (%) | Units Per m Squared | Pack Size | Characteristic Unconfined Compressive Strength (fuc) (Mpa) | Cold Water Absorption (%) | Initial Rate of Absorption (IRA) | eFactor | Durability Class | Liability to Effloresce | Lime Pitting Liability | Solar Absorptance Rating |
|---------------|--------------|---|---|-------|-------------|------------|-------------|----------------------|---------------------------|-----------------|---------------------|-----------|--|---------------------------|----------------------------------|---------|------------------|-------------------------|------------------------|--------------------------|
| Panorama 50 | Snowfield |  |  | QLD | 390 | 110 | 50 | DW2 | 2.9 | <38 | 41.66 | 348 | >13 | <10 | 1.0 - 3.0 | <1.0 | General Purpose | Slight | Nil | - |
| Panorama 50 | Night Sky |  |  | QLD | 390 | 110 | 50 | DW2 | 2.9 | <38 | 41.66 | 348 | >13 | <8 | 1.0 - 3.0 | <1.0 | Exposure Grade | Slight | Nil | - |
| Panorama 50 | Midnight |  |  | QLD | 390 | 110 | 50 | DW2 | 2.9 | <38 | 41.66 | 348 | >13 | <8 | 1.0 - 3.0 | <1.0 | Exposure Grade | Slight | Nil | - |
| Panorama 50 | Lunar Crust |  |  | QLD | 390 | 110 | 50 | DW2 | 2.9 | <38 | 41.66 | 348 | >13 | <8 | 1.0 - 3.0 | <1.0 | Exposure Grade | Slight | Nil | - |

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

February 2022