


Product Range: Panorama 50

Product Name: Snowfield | Size: 390 × 110 × 50mm | Manufactured: QLD




Typical Properties	
Length (mm)	390mm
Width (mm)	110mm
Height (mm)	50mm
Dimensional Category	DW2
Average Weight / Unit (kg)	2.9
Units per Square Metre	41.66
Pack Size	348
Characteristic Unconfined Compressive Strength (f'uc) MPa	>13
Maximum Cold Water Absorption (%)	<10
Initial Rate of Absorption (IRA) (kg/m ² min)	1.0 - 3.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	<38
Liability to Efflorescence	Slight
Lime Pitting Liability	Nil
Solar Absorptance Rating	-
Durability Class	General Purpose

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 October 2020

Product Range: Panorama 50

Product Name: Night Sky | Size: 390 × 110 × 50mm | Manufactured: QLD




Typical Properties	
Length (mm)	390mm
Width (mm)	110mm
Height (mm)	50mm
Dimensional Category	DW2
Average Weight / Unit (kg)	2.9
Units per Square Metre	41.66
Pack Size	348
Characteristic Unconfined Compressive Strength (f'uc) MPa	>13
Maximum Cold Water Absorption (%)	<8
Initial Rate of Absorption (IRA) (kg/m ² min)	1.0 - 3.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	<38
Liability to Efflorescence	Slight
Lime Pitting Liability	Nil
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 October 2020

Product Range: Panorama 50

Product Name: Midnight | Size: 390 × 110 × 50mm | Manufactured: QLD




Typical Properties	
Length (mm)	390mm
Width (mm)	110mm
Height (mm)	50mm
Dimensional Category	DW2
Average Weight / Unit (kg)	2.9
Units per Square Metre	41.66
Pack Size	348
Characteristic Unconfined Compressive Strength (f'uc) MPa	>13
Maximum Cold Water Absorption (%)	<8
Initial Rate of Absorption (IRA) (kg/m ² min)	1.0 - 3.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	<38
Liability to Efflorescence	Slight
Lime Pitting Liability	Nil
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 October 2020

Product Range: Panorama 50

Product Name: Lunar Crust | **Size:** 390 × 110 × 50mm | **Manufactured:** QLD




Typical Properties	
Length (mm)	390mm
Width (mm)	110mm
Height (mm)	50mm
Dimensional Category	DW2
Average Weight / Unit (kg)	2.9
Units per Square Metre	41.66
Pack Size	348
Characteristic Unconfined Compressive Strength (f'uc) MPa	>13
Maximum Cold Water Absorption (%)	<8
Initial Rate of Absorption (IRA) (kg/m ² min)	1.0 - 3.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	<38
Liability to Efflorescence	Slight
Lime Pitting Liability	Nil
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 October 2020

Product Range: Panorama 50

Product Name: Evening Dusk | **Size:** 390 × 110 × 50mm | **Manufactured:** QLD



Typical Properties	
Length (mm)	390mm
Width (mm)	110mm
Height (mm)	50mm
Dimensional Category	DW2
Average Weight / Unit (kg)	2.9
Units per Square Metre	41.66
Pack Size	348
Characteristic Unconfined Compressive Strength (f'uc) MPa	>13
Maximum Cold Water Absorption (%)	<8
Initial Rate of Absorption (IRA) (kg/m ² min)	1.0 - 3.0
Coefficient of Expansion e'Factor (mm/m)	<1.0
Core Volume (%)	<38
Liability to Efflorescence	Slight
Lime Pitting Liability	Nil
Solar Absorptance Rating	-
Durability Class	Exposure Grade

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 October 2020