

Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Estate	Ashford (Block)			WA	290	90	162	DW2	5.2	<40	18.5	138	>12	<10	<2.0	<1.0	Exposure Grade	Slight	Nil	-
Estate	Belhaven (Block)			WA	290	90	162	DW2	5.2	<40	18.5	138	>12	<10	<2.0	<1.0	Exposure Grade	Slight	Nil	-
Estate	Halliday (Block)			WA	290	90	162	DW2	5.8	<40	18.5	138	>12	<9	<2.0	<0.9	Exposure Grade	Slight	Nil	-
Estate	Mansfield (Block)			WA	290	90	162	DW2	5.2	<40	18.5	138	>12	<10	<2.0	<1.0	Exposure Grade	Slight	Nil	-
Estate	Whitfield (Block)			WA	290	90	162	DW2	5.2	<40	18.5	138	>12	<10	<2.0	<1.0	Exposure Grade	Slight	Nil	-
Estate	Ashford (Aspect)			WA	290	90	76	DW2	2.8	<40	37	276	>12	<10	<2.0	<1.0	Exposure Grade	Slight	Nil	-
Estate	Belhaven (Aspect)			WA	290	90	76	DW2	2.8	<40	37	276	>12	<10	<2.0	<1.0	Exposure Grade	Slight	Nil	-
Estate	Halliday (Aspect)			WA	290	90	76	DW2	2.8	<40	37	276	>12	<9	<2.0	<0.9	Exposure Grade	Slight	Nil	-
Estate	Mansfield (Aspect)			WA	290	90	76	DW2	2.8	<40	37	276	>12	<10	<2.0	<1.0	Exposure Grade	Slight	Nil	-
Estate	Whitfield (Aspect)			WA	290	90	76	DW2	2.8	<40	37	276	>12	<10	<2.0	<1.0	Exposure Grade	Slight	Nil	-

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

November 2021