

Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	Division	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
La Paloma	Azul			Import	230	110	76	DW1	2.8	<40	48.5	432	>15	<8	<1.0	<1.2	Exposure Grade	Slight	Slight	Dark
La Paloma	Azul			Import	230	110	50	DW1	1.8	<40	69.5	648	>15	<8	<1.0	<1.2	Exposure Grade	Slight	Slight	Dark
La Paloma	Castellana			Import	230	110	76	DW1	2.8	<40	48.5	432	>15	<10	<1.0	<1.2	Exposure Grade	Slight	Slight	Light
La Paloma	Castellana			Import	230	110	50	DW1	1.8	<40	69.5	648	>15	<10	<1.0	<1.2	Exposure Grade	Slight	Slight	Light
La Paloma	Castellana			Import	290	110	50	DW1	2.3	<40	56	459	>15	<10	<1.0	<1.2	Exposure Grade	Slight	Slight	Light
La Paloma	Gaudi Rustico			Import	480	100	40	DW1	4.9	<40	35	240	>15	<10	<1.0	<1.2	Exposure Grade	Slight	Slight	Dark
La Paloma	Miro			Import	230	110	76	DW1	2.8	<40	48.5	432	>15	<10	<1.0	<1.2	Exposure Grade	Slight	Slight	Light
La Paloma	Miro			Import	230	110	50	DW1	1.8	<40	69.5	648	>15	<10	<1.0	<1.2	Exposure Grade	Slight	Slight	Light
La Paloma	Miro			Import	290	110	50	DW1	2.3	<40	56	459	>15	<10	<1.0	<1.2	Exposure Grade	Slight	Slight	Light
La Paloma	Miro Rustico			Import	470	100	40	DW1	4.9	<40	35	240	>15	<10	<1.0	<1.2	Exposure Grade	Slight	Slight	Light
La Paloma	Romero			Import	230	110	76	DW1	2.8	<40	48.5	432	>15	<8	<1.0	<1.2	Exposure Grade	Slight	Slight	Dark
La Paloma	Romero			Import	230	110	50	DW1	1.8	<40	69.5	648	>15	<8	<1.0	<1.2	Exposure Grade	Slight	Slight	Dark
La Paloma	Romero			Import	290	110	50	DW1	2.3	<40	56	459	>15	<8	<1.0	<1.2	Exposure Grade	Slight	Slight	Dark

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 March 2021



BOWRAL BRICKS



nubrik
authentic brickwork