

Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/Unit (kg)	Units Per m Squared	Pack Size	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorption	LRV	BASIX Rating
Thin Brick	San Selmo Reclaimed																			
	Limewash Corner Unit			Import	230	110	76	DW0	1.0	NA	1008	<17	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.54	51.9	Medium
	Limewash Facing Unit			Import	230	18	76	DW0	0.7	48.5	2160	<17	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.54	51.9	Medium
Thin Brick	San Selmo Reclaimed																			
	Reclaimed Original Corner Unit			Import	230	110	76	DW0	1.0	NA	1008	<17	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.46	34.7	Light
	Reclaimed Original Facing Unit			Import	230	18	76	DW0	0.7	48.5	2160	<17	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.46	34.7	Light
Thin Brick	San Selmo Reclaimed																			
	Aged Red Corner Unit			Import	230	110	76	DW0	1.0	NA	1008	<17	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.68	22.2	Medium
	Aged Red Facing Unit			Import	230	18	76	DW0	0.7	48.5	2160	<17	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.68	22.2	Medium
Thin Brick	San Selmo Smoked																			
	Cloudy Silver Corner Unit			Import	230	110	76	DW0	1.0	NA	1008	<15	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.51	22.8	Medium
	Cloudy Silver Facing Unit			Import	230	18	76	DW0	0.7	48.5	2160	<15	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.51	22.8	Medium
Thin Brick	San Selmo Smoked																			
	Grey Cashmere Corner Unit			Import	230	110	76	DW0	1.0	NA	1008	<15	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.54	45.5	Medium
	Grey Cashmere Facing Unit			Import	230	18	76	DW0	0.7	48.5	2160	<15	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.54	45.5	Medium
Thin Brick	San Selmo Smoked																			
	Opaque Slate Corner Unit			Import	230	110	76	DW0	1.0	NA	1008	<15	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.68	24.9	Medium
	Opaque Slate Facing Unit			Import	230	18	76	DW0	0.7	48.5	2160	<15	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.68	24.9	Medium
Thin Brick	San Selmo Smoked																			
	Wild Storm Corner Unit			Import	230	110	76	DW0	1.0	NA	1008	<15	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.82	14.1	Dark
	Wild Storm Facing Unit			Import	230	18	76	DW0	0.7	48.5	2160	<15	4.0 - 8.0	<1.0	General Purpose	Slight	Slight	0.82	14.1	Dark

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

November 2021

Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Units Per m Squared	Pack Size	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorption	LRV	BASIX Rating
Thin Brick	La Paloma Castellana <i>Corner Unit</i>			Import	230	110	76	DW1	1.1	NA	1200	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.13	67.0	Light
	Castellana <i>Facing Unit</i>			Import	230	18	76	DW1	0.7	48.5	1920	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.13	67.0	Light
Thin Brick	La Paloma Miro <i>Corner Unit</i>			Import	230	110	76	DW1	1.1	NA	1200	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.23	63.7	Light
	Miro <i>Facing Unit</i>			Import	230	18	76	DW1	0.7	48.5	1920	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.23	63.7	Light
Thin Brick	La Paloma Azul <i>Corner Unit</i>			Import	230	110	76	DW1	1.1	NA	1200	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.83	13.1	Dark
	Azul <i>Facing Unit</i>			Import	230	18	76	DW1	0.7	48.5	1920	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.83	13.1	Dark
Thin Brick	La Paloma Romero <i>Corner Unit</i>			Import	230	110	76	DW1	1.1	NA	1200	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.85	12.0	Dark
	Romero <i>Facing Unit</i>			Import	230	18	76	DW1	0.7	48.5	1920	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.85	12.0	Dark
Thin Brick	La Paloma Glazed White <i>Corner Unit</i>			Import	230	110	76	DW1	1.1	NA	1200	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.34	66.4	Light
	White <i>Facing Unit</i>			Import	230	18	76	DW1	0.7	48.5	1920	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.34	66.4	Light
Thin Brick	La Paloma Glazed Black <i>Corner Unit</i>			Import	230	110	76	DW1	1.1	NA	1200	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.9	1.0	Dark
	Black <i>Facing Unit</i>			Import	230	18	76	DW1	0.7	48.5	1920	<6	<0.8	<1.0	Exposure Grade	Slight	Nil	0.9	1.0	Dark

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

November 2021