

# Technical Data Sheet

**BRICKWORKS**

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/Unit (kg)	Core Volume (%)	Units Per m <sup>2</sup>	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorption Rating	LRV	BASIX Rating
Burlesque	Brushed Leather			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.58	23.0	Medium
Burlesque	Bursting Orange			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.57	23.0	Medium
Burlesque	Charming Black			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.90	1.0	Dark
Burlesque	Cognac Illusion			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.67	14.0	Medium
Burlesque	Deepening Green			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.59	15.0	Medium
Burlesque	Enchanting Yellow			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.44	48.0	Light
Burlesque	Indulgent White			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.34	62.0	Light
Burlesque	Karrington Silver			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.54	30.0	Medium
Burlesque	Luscious Red			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.62	8.0	Medium
Burlesque	Majestic Grey			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.50	36.0	Medium
Burlesque	Oyster Grey			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.56	28.0	Medium
Burlesque	Smashing Blue			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.83	2.0	Dark
Burlesque	Sublime Steel			NSW	230	110	76	DW1	2.7	<40	48.5	512	>20	<10	0.1 - 0.8	<0.8	Exposure Grade	Slight	Slight	0.67	17.0	Medium

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

March 2022

 australbricks®