













Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/Unit (kg)	Units per m ²	Pack Size	Cold Water Absorption (%)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Breaking Load (kN)	Modulus of Rupture (Mpa)	Abrasion Resistance (cm ³)	Slip Resistance	Solar Absorption	LRV	BASIX Rating
London	Bowral Blue			NSW	230	114	65	DPA2	3.6	37	500	<10	<0.8	Exposure Grade	Slight	Slight	>10	<6	<7	P5	0.84	7.8	Dark
London	Brahman Granite			NSW	230	114	65	DPA2	3.6	37	500	<10	<0.8	Exposure Grade	Slight	Slight	>10	<6	<7	P5	0.78	10.0	Dark
London	Chestnut			NSW	230	114	65	DPA2	3.6	37	500	<15	<1.0	Exposure Grade	Slight	Slight	>10	<6	<15	P5	0.81	11.4	Dark
London	Maple			NSW	230	114	65	DPA2	3.6	37	500	<10	<0.8	Exposure Grade	Slight	Slight	>10	<6	<15	P5	0.81	14.1	Dark
London	Regency Grey			NSW	230	114	65	DPA2	3.6	37	500	<15	<1.0	Exposure Grade	Slight	Slight	>10	<6	<7	P5	0.68	18.0	Medium
London	Silver Sand			NSW	230	114	65	DPA2	3.6	37	500	<12	<1.0	Exposure Grade	Slight	Slight	>8	<5	<15	P5	0.58	33.3	Medium

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

July 2022

BOWRAL BRICKS