

# Technical Data Sheet

**BRICKWORKS**

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Australis	Coorong			VIC	230	110	76	DW1	2.8	Solid	48.5	400	>20	<10	0.5-1.5	<1.0	Exposure Grade	Slight	Slight	0.33
Australis	Hotham Peak			VIC	230	110	76	DW1	2.8	Solid	48.5	400	>20	<10	0.5-1.5	<1.0	Exposure Grade	Slight	Slight	0.37
Australis	Murray Sunset			VIC	230	110	76	DW1	2.8	Solid	48.5	400	>20	<10	0.5-1.5	<1.0	Exposure Grade	Slight	Slight	0.34
Australis	Wave Rock			VIC	230	110	76	DW1	2.8	Solid	48.5	400	>20	<10	0.5-1.5	<1.0	Exposure Grade	Slight	Slight	0.32

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.  
 October 2021

**NUBRİK**