

















# Technical Data Sheet

**BRICKWORKS**

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Bowral Highlands	Bangadilly			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	<15	4.0-6.0	<1.0	Exposure Grade	Slight	Slight	0.56
Bowral Highlands	Jellore			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	<15	4.0-6.0	<1.0	Exposure Grade	Slight	Slight	0.42
Bowral Highlands	Meryla			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	<15	4.0-6.0	<1.0	Exposure Grade	Slight	Slight	0.40
Bowral Highlands	Natti			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	<15	4.0-6.0	<1.0	Exposure Grade	Slight	Slight	TBA
Bowral Highlands	Penrose			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	<15	4.0-6.0	<1.0	Exposure Grade	Slight	Slight	TBA
Bowral Highlands	Tarlo			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	<15	4.0-6.0	<1.0	Exposure Grade	Slight	Slight	0.37
Bowral Highlands	Wingello			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	<15	4.0-6.0	<1.0	Exposure Grade	Slight	Slight	0.51
Bowral Highlands	Woodlands			NSW	230	110	76	DW1	3.8	Solid	48.5	384	>8	<15	4.0-6.0	<1.0	Exposure Grade	Slight	Slight	0.50

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

October 2021

**BOWRAL BRICKS**