















Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Bowral Remastered	Gibraltar			NSW	230	110	76	DW1	3.8	Solid	48.5	400	>8	<15	3.0-8.0	<1.0	Exposure Grade	Slight	Slight	TBC
Bowral Remastered	Hume			NSW	230	110	76	DW1	3.8	Solid	48.5	400	>8	<15	3.0-8.0	<1.0	Exposure Grade	Slight	Slight	TBC
Bowral Remastered	Moss Vale			NSW	230	110	76	DW1	3.8	Solid	48.5	400	>8	<15	3.0-8.0	<1.0	Exposure Grade	Slight	Slight	TBC
Bowral Remastered	Oxley			NSW	230	110	76	DW1	3.8	Solid	48.5	400	>8	<15	3.0-8.0	<1.0	Exposure Grade	Slight	Slight	TBC
Bowral Remastered	St Jude			NSW	230	110	76	DW1	3.8	Solid	48.5	400	>8	<15	3.0-8.0	<1.0	Exposure Grade	Slight	Slight	TBC
Bowral Remastered	St Simon			NSW	230	110	76	DW1	3.8	Solid	48.5	400	>8	<15	3.0-8.0	<1.0	Exposure Grade	Slight	Slight	TBC
Bowral Remastered	Westow			NSW	230	110	76	DW1	3.8	Solid	48.5	400	>8	<15	3.0-8.0	<1.0	Exposure Grade	Slight	Slight	TBC
Bowral Remastered	Wingecaribee			NSW	230	110	76	DW1	3.8	Solid	48.5	400	>8	<15	3.0-8.0	<1.0	Exposure Grade	Slight	Slight	TBC

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

July 2021



BOWRAL BRICKS



nubrik[®]
authentic brickwork