BRICKWORKS

Technical Data Sheet

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating	LRV	BASIX Rating
Laneway	Brunswick Blue			VIC	230	110	76	DWO	4.1	<10	48.5	400	>12	<10	0.5 - 2.5	<1.2	Exposure Grade	Slight	Slight	0.73	15.0	Dark
Laneway	Hardware Grey	\bigcirc		VIC	230	110	76	DWO	4.1	<10	48.5	400	>12	<10	0.5 - 2.5	<1.2	Exposure Grade	Slight	Slight	0.55	20.0	Dark
Laneway	Hosier Bluestone			VIC	230	110	76	DWO	4.1	<10	48.5	400	>12	<10	0.5 - 2.5	<1.2	Exposure Grade	Slight	Slight	0.51	28.0	Dark

This Data represents average results from commercial production lots. If specific test results are required, sample should be taken from current production lots. AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.