



























Technical Data Sheet

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorption	LRV	BASIX Rating
Sculptured Sands	Granite (NATURAL)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	General Purpose	Slight	Slight	0.62	21.9	Medium
Sculptured Sands	Arenite (OPAQUE)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	General Purpose	Slight	Slight	0.59	35.2	Medium
Sculptured Sands	Beach (NATURAL)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	General Purpose	Slight	Slight	0.50	26.4	Medium
Sculptured Sands	Quartz (OPAQUE)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	General Purpose	Slight	Slight	0.55	26.5	Medium
Sculptured Sands	Dolomite (NATURAL)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	Exposure Grade	Slight	Slight	0.71	16.5	Dark
Sculptured Sands	Olivine (OPAQUE)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	Exposure Grade	Slight	Slight	0.64	20.0	Medium
Sculptured Sands	Volcanic Ash (NATURAL)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	Exposure Grade	Slight	Slight	0.73	12.6	Dark
Sculptured Sands	Pumice (OPAQUE)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	Exposure Grade	Slight	Slight	0.75	18.7	Dark
Sculptured Sands	Siltstone (NATURAL)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	General Purpose	Slight	Slight	0.80	8.4	Dark
Sculptured Sands	Rockaway (OPAQUE)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	Exposure Grade	Slight	Slight	0.74	18.1	Dark
Sculptured Sands	Ochre (NATURAL)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	Exposure Grade	Slight	Slight	0.85	9.1	Dark
Sculptured Sands	Calcite (OPAQUE)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	Exposure Grade	Slight	Slight	0.63	21.6	Medium
Sculptured Sands	Magnetite (NATURAL)			NSW	230	110	76	DW0	3.4	Solid	48.5	400	>5	<15	1.0-5.0	<1.0	Exposure Grade	Slight	Slight	0.83	6.6	Dark

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

November 2021