

Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Panorama	Evening Dusk			NSW	390	110	76	DW2	4.4	<38	29.06	312	>13	<8	1.0-3.0	<1.0	Exposure Grade	Slight	Nil	-
Panorama	Lunar Crust			NSW	390	110	76	DW2	4.4	<38	29.06	312	>13	<8	1.0-3.0	<1.0	Exposure Grade	Slight	Nil	-
Panorama	Midnight			NSW	390	110	76	DW2	4.4	<38	29.06	312	>13	<8	1.0-3.0	<1.0	Exposure Grade	Slight	Nil	-
Panorama	Night Sky			NSW	390	110	76	DW1	4.4	<38	29.06	312	>13	<8	1.0-3.0	<1.0	Exposure Grade	Slight	Nil	-
Panorama	Snowfield			NSW	390	110	76	DW2	4.4	<38	29.06	312	>13	<8	1.0-3.0	<1.0	General Purpose	Slight	Nil	-

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 August 2021



BOWRAL BRICKS



nubrik
authentic brickwork