











Technical Data Sheet

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating	LRV	BASIX Rating
Urban One	Chiffon			NSW	230	110	76	DW1	2.7	<40	48.5	400	<15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	0.74	15.3	Dark
Urban One	Pepper			NSW	230	110	76	DW1	2.7	<40	48.5	400	<15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	0.76	13.7	Dark
Urban One	Silver			NSW	230	110	76	DW1	2.7	<40	48.5	400	<15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	0.58	31.2	Medium
Urban One	Latte			NSW	230	110	76	DW1	2.7	<40	48.5	400	<15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	0.67	19.0	Medium
Urban One	Praline			NSW	230	110	76	DW1	2.7	<40	48.5	400	<15	<10	0.1-1.0	<1.0	Exposure Grade	Slight	Slight	0.53	30.1	Medium

This Data represents average results from commercial production lots.
 If specific test results are required, sample should be taken from current production lots.
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.
 October 2021