

Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight/ Unit (kg)	Core Volume (%)	Units Per m Squared	Pack Size	Characteristic Unconfined Compressive Strength (fuc) (Mpa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA)	eFactor	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
Venetian Glass	Aqua Marine (NATURAL)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Aqua Marine (POLISHED)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Aqua Marine (FROSTED)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Aqua Marine (SATIN)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Arctic Crystal (NATURAL)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Arctic Crystal (POLISHED)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Arctic Crystal (FROSTED)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Arctic Crystal (SATIN)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Golden Amber (NATURAL)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Golden Amber (POLISHED)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Golden Amber (FROSTED)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Golden Amber (SATIN)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Blue Sapphire (NATURAL)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Blue Sapphire (POLISHED)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Blue Sapphire (FROSTED)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Blue Sapphire (SATIN)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Smokey Quartz (NATURAL)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Smokey Quartz (POLISHED)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Smokey Quartz (FROSTED)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A
Venetian Glass	Smokey Quartz (SATIN)			NSW	230	110	76	DW1	4.7	Solid	48.5	216	>30	0	0	0	Exposure Grade	Nil	Nil	N/A

This Data represents average results from commercial production lots.

If specific test results are required, sample should be taken from current production lots.

AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

April 2021



BORAL BRICKS



nubrik
authentic brickwork