

Product Details

range name	BREEZE BLOCKS
finish	HONED
colours	PORCELAIN NICKEL PEWTER
product code description	10.908 FLOWER BREEZE

Properties and Specifications

nominal dimensions (length x width x height mm)	300 × 100 × 300mm
actual dimensions (length x width x height mm)	290 × 90 × 290mm
core volume (% overall thickness)	36
characteristic unconfined compressive strength (MPa)	5
minimum shell thickness (mm)	-
average weight (KG)	9.4
average number per tonne	-
number per pallet	128
number per sqm/lm	11.11
durability class (to AS4456.10 - sodium sulphate and sodium chloride)	Exposure Grade
wall mass inc mortar hollow	-
CWA	7%
IRA	1.9

Diagram



This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.

^When reinforced and Srf <36: 240 minutes

Product Details

range name	BREEZE BLOCKS
finish	HONED
colours	PORCELAIN NICKEL PEWTER
product code description	10.906 CIRCLE BREEZE

Properties and Specifications

nominal dimensions (length x width x height mm)	300 × 100 × 300mm
actual dimensions (length x width x height mm)	290 × 90 × 290mm
core volume (% overall thickness)	48
characteristic unconfined compressive strength (MPa)	3
minimum shell thickness (mm)	-
average weight (KG)	9.2
average number per tonne	-
number per pallet	128
number per sqm/lm	11.9
durability class (to AS4456.10 - sodium sulphate and sodium chloride)	Exposure Grade
wall mass inc mortar hollow	-
CWA	7%
IRA	1.9

Diagram



This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.

^When reinforced and Srf <36: 240 minutes

Product Details

range name	BREEZE BLOCKS
finish	HONED
colours	PORCELAIN NICKEL PEWTER
product code description	10.938 CLOUD BREEZE

Properties and Specifications

nominal dimensions (length x width x height mm)	400 × 100 × 200mm
actual dimensions (length x width x height mm)	390 × 90 × 190mm
core volume (% overall thickness)	43
characteristic unconfined compressive strength (MPa)	3
minimum shell thickness (mm)	-
average weight (KG)	8.3
average number per tonne	-
number per pallet	144
number per sqm/lm	12.5
durability class (to AS4456.10 - sodium sulphate and sodium chloride)	Exposure Grade
wall mass inc mortar hollow	-
CWA	7%
IRA	1.9

Diagram



This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.

^When reinforced and Srf <36: 240 minutes

Product Details

range name	BREEZE BLOCKS
finish	HONED
colours	PORCELAIN NICKEL PEWTER
product code description	15.936 DIAMOND BREEZE

Properties and Specifications

nominal dimensions (length x width x height mm)	400 × 150 × 200mm
actual dimensions (length x width x height mm)	390 × 140 × 190mm
core volume (% overall thickness)	45
characteristic unconfined compressive strength (MPa)	4
minimum shell thickness (mm)	25
average weight (KG)	12.5
average number per tonne	-
number per pallet	108
number per sqm/lm	12.5
durability class (to AS4456.10 - sodium sulphate and sodium chloride)	Exposure Grade
wall mass inc mortar hollow	173
CWA	7
IRA	1.9

Diagram



This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.

^When reinforced and Srf <36: 240 minutes

Product Details

range name	BREEZE BLOCKS
finish	HONED
colours	PORCELAIN NICKEL PEWTER
product code description	15.937 WEDGE BREEZE

Properties and Specifications

nominal dimensions (length x width x height mm)	400 × 150 × 200mm
actual dimensions (length x width x height mm)	390 × 140 × 190mm
core volume (% overall thickness)	45
characteristic unconfined compressive strength (MPa)	7
minimum shell thickness (mm)	25
average weight (KG)	12.2
average number per tonne	-
number per pallet	108
number per sqm/lm	12.5
durability class (to AS4456.10 - sodium sulphate and sodium chloride)	Exposure Grade
wall mass inc mortar hollow	173
CWA	7%
IRA	1.9

Diagram



This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.

^When reinforced and Srf <36: 240 minutes

Product Details

range name	BREEZE BLOCKS
finish	HONED
colours	PORCELAIN NICKEL PEWTER
product code description	20.414 ARC BREEZE

Properties and Specifications

nominal dimensions (length x width x height mm)	400 × 190 × 200mm
actual dimensions (length x width x height mm)	390 × 180 × 190mm
core volume (% overall thickness)	47
characteristic unconfined compressive strength (MPa)	6
minimum shell thickness (mm)	-
average weight (KG)	14.5
average number per tonne	-
number per pallet	90
number per sqm/lm	12.5
durability class (to AS4456.10 - sodium sulphate and sodium chloride)	Exposure Grade
wall mass inc mortar hollow	-
CWA	7%
IRA	1.9

Diagram



This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.

^When reinforced and Srf <36: 240 minutes

Product Details

range name	BREEZE BLOCKS
finish	HONED
colours	PORCELAIN NICKEL PEWTER
product code description	10.960 LINEAR BREEZE

Properties and Specifications

actual dimensions (length x width x height mm)	390 × 84 × 90mm
core volume (% overall thickness)	33
characteristic unconfined compressive strength (MPa)	3
minimum shell thickness (mm)	-
average weight (KG)	4.7
average number per tonne	-
number per pallet	-
number per sqm/lm	25
durability class (to AS4456.10 - sodium sulphate and sodium chloride)	Exposure Grade
wall mass inc mortar hollow	-
CWA	7
IRA	1.9

Diagram



This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact us for confirmation of product specification. Tested as per AS/NZS 4455.1: 2008 and 4456: 2003. Fire resistance levels as per AS3700: 2018. Acoustic opinion derived from Day Design Pty Ltd. 2012. Tested in accordance with AS 1191:1001 and AS/NZS 1276.1:1999.

^When reinforced and Srf <36: 240 minutes