


Product Details

| | |
|----------------------------|-------------------------------|
| range name | PERCORSI SMART by KEOPE |
| finish | TEXTURED |
| colours | PIETRA DI BAGNOLO |
| product code description | ### 600 X 600 X 20MM PAVERS |

Properties and Specifications

| | |
|--|------------------|
| actual dimensions (length x width x height mm) | 600 X 600 X 20MM |
| dimensional category | DPA2 |
| average weight (KG) | 16.9 |
| durability class | General Purpose |
| number per sqm/lm | 2.78 |
| number per pallet | - |
| characteristics breaking load (kN) | 13 |
| mean cold water absorption (%) | 0.5 |
| mean abrasion resistance (CM ³) | 7.4 |
| slip resistance category | P5 |
| modulus of rupture (MPa) | 35 |
| | - |
| | - |

Diagram



Tested as per AS/NZS 4456: 2003 and 4586: 2013.

This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact UrbanStone for confirmation of product specification


Product Details

| | |
|----------------------------|-------------------------------|
| range name | PERCORSI QUARTZ by KEOPE |
| finish | TEXTURED |
| colours | WHITE BLACK |
| product code description | ### 600 X 600 X 20MM PAVERS |

Properties and Specifications

| | |
|--|------------------|
| actual dimensions (length x width x height mm) | 600 X 600 X 20MM |
| dimensional category | DPA2 |
| average weight (KG) | 16.9 |
| durability class | General Purpose |
| number per sqm/lm | 2.78 |
| number per pallet | - |
| characteristics breaking load (kN) | 13 |
| mean cold water absorption (%) | 0.5 |
| mean abrasion resistance (CM ³) | 7.4 |
| slip resistance category | P5 |
| modulus of rupture (MPa) | 35 |
| | - |
| | - |

Diagram



Tested as per AS/NZS 4456: 2003 and 4586: 2013.

This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact UrbanStone for confirmation of product specification


Product Details

| | |
|----------------------------|-----------------------------------|
| range name | PERCORSI EXTRA by KEOPE |
| finish | TEXTURED |
| colours | PIETRA DI COMBE PIETRA DI BARGE |
| product code description | ### 600 X 600 X 20MM PAVERS |

Properties and Specifications

| | |
|--|------------------|
| actual dimensions (length x width x height mm) | 600 X 600 X 20MM |
| dimensional category | DPA2 |
| average weight (KG) | 16.9 |
| durability class | General Purpose |
| number per sqm/lm | 2.78 |
| number per pallet | - |
| characteristics breaking load (kN) | 13 |
| mean cold water absorption (%) | 0.5 |
| mean abrasion resistance (CM ³) | 7.4 |
| slip resistance category | P5 |
| modulus of rupture (MPa) | 35 |
| | - |
| | - |

Diagram



Tested as per AS/NZS 4456: 2003 and 4586: 2013.

This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact UrbanStone for confirmation of product specification


Product Details

| | |
|----------------------------|--------------------------------|
| range name | SOUL by KEOPE |
| finish | TEXTURED |
| colours | WALNUT GREY |
| product code description | ### 1200 X 300 X 20MM PAVERS |

Properties and Specifications

| | |
|--|-------------------|
| actual dimensions (length x width x height mm) | 1200 X 300 X 20MM |
| dimensional category | DPA2 |
| average weight (KG) | 15 |
| durability class | General Purpose |
| number per sqm/lm | 2.78 |
| number per pallet | - |
| characteristics breaking load (kN) | 13 |
| mean cold water absorption (%) | 0.5 |
| mean abrasion resistance (CM ³) | 7.4 |
| slip resistance category | P5 |
| modulus of rupture (MPa) | 35 |
| | - |
| | - |

Diagram



Tested as per AS/NZS 4456: 2003 and 4586: 2013.

This data represents average results from production lots based on the results achieved by samples selected at random for testing. Figures are accurate at date of publication and subject to change without notice. Contact UrbanStone for confirmation of product specification